

HOT SPLICING AND REPAIR MATERIAL

Hot splicing and repair products

Intermediate rubber STZ NL, uncured

Red protection foil (poly).



538 0605

Specifications

Polymer basis	NR/BR/SBR	DIN ISO 1629
Specific weight	1.18 g/cm ³	DIN EN ISO 1183-1
Hardness	65 Shore A	DIN ISO 7619-1
Colour	Black	

Ref. No.	Designation	Dimensions
538 0605	Intermediate rubber STZ NL, uncured	0.5 x 500 x 33 000 mm
538 0611	Intermediate rubber STZ NL, uncured	1 x 500 x 16 400 mm
538 0622	Intermediate rubber STZ NL, uncured	2 x 500 x 8 200 mm
538 0644	Intermediate rubber STZ NL, uncured	2 x 1 400 x 23 000 mm